

BLISTER FREE 66

Defoamer for solvent borne coating systems

Chemical base: Special combination of surface active compounds

Properties: **BLISTER FREE 66** has a strong influence on the interfaces of organic systems. The formation of air bubbles during manufacture and application is prevented and entrapped air as well as bubbles are quickly destroyed. Defoaming is promoted and defects like pinholes and craters are avoided. In wax containing polyester coatings **BLISTER FREE 66** will improve the streak free floatation and distribution of the wax on the surface.

Applications: **BLISTER FREE 66** is especially suitable in polyesters, polyurethanes and acrylic systems. **BLISTER FREE 66** can be used as a defoaming additive in nearly all solvent borne coating systems.

Technical data:
(Guide values)

Appearance	:	colourless to light yellowish liquid
Density (ISO 2811-1)	:	0.90 g/cm ³
Flash point (ISO 1523)	:	31 °C
Active matter	:	100 %

Processing: **BLISTER FREE 66** must be thoroughly incorporated and it is therefore advisable to add it at the beginning of production. In pigmented systems **BLISTER FREE 66** should be added before milling. The dosage is between 0.1 - 1.0 % , calculated on total system.

Storage: Stir **BLISTER FREE 66** up before use. Keep it in a cool, well-ventilated place. Subject to appropriate storage, the described properties of **BLISTER FREE 66** remain stable for at least 12 months, provided the original container is closed after use.

Packaging: 25 kg drum

The above information is based on our current knowledge and experience. No binding assurance in respect of certain properties or suitability for certain applications must be read into our information. Patent rights and other proprietary rights must be observed if necessary.
Further safety instructions please learn from our material safety data sheet. 03/2019